

NF A49-150-85 STEEL TUBES WELDED TUBES INTENDED TO BE COATED OF PROTECTED FOR USE IN WATER PIPING SYSTEMS

1. Chemical Composition

Grade	Mfg. Process	Chemical Composition (%)								
		C	Si	Mn	P	S	Ni	Cr	Mo	Others
TSE235	W	0.16Max	-	1.10Max	0.040Max	0.045Max	-	-	-	-

2. Mechanical Properties

Grade	Tensile Test MPa or N/mm ²		Remarks
	Min Yield point	Tensile Strength	
TSE235	235	360Min	(STPG370)

JIS Number and Corresponding Foreign Standards

JIS			ASTM			BS			DIN			NF			ISO			Index Number	
Standard Number	Grade	Type	Standard Number	Grade	Type	Standard Number	Grade	Type	Standard Number	Grade	Type	Standard Number	Grade	Type	Standard Number	Grade	Type		
G3454	STPG370 (STPG38)	C	A135	Gr A	C	3601	ERW360	C	1626	St37.0	C	A49-112	TS27b	C	559	TS4	C	C002	
			A587	-	C	"	S360	C	1629	St37.0	C	A49-141	TS37a	C	2604/2	TS4	C		
										17172	StE210.7	C	A49-142	TS37a	C	2604/3	TW4		C
													"	TS37b	C				
													A49-150	TSE235	C				
													A49-212	TS37c	C				
													A49-242	TS37c	C				
													A49-250	TAE24a	C				
													A49-400	TSE220	C				
		G3454	STPG410 (STPG42)	C	A135	GrB	C	3601	ERW410	C	1626	St44.0	C	A49-112	TS42b	C	559		TS9
	A524			-	C	"	S410	C				A49-141	TS42b	C	2604/2	TW9	C		
												A49-212	TS42c	C	2604/3	TW9	C		

												A49-242	TS42c	C	3183	E24-1	C	
												A49-250	TSE26b	C	"	E24-2		
												A49-400	TSE250	C				